SHIMS & SEALANTS

flamemaster

SOCOMORE Aerospace Sealants



CS 247

Aircraft windshield sealant

SAMPLES AVAILABLE

Features

- Good adhesion on various substrates
- Solid black color
- Faster cure than CS 3247
- 98% NVM, minimum
- No APEO surfactants
- Terphenyl free
- No aromatic solvents

	Tack-free time (hours)	**Cure time to 30A** (hours)
B-1/2	< 4	< 12
B-2	< 5	< 32



Description

- Two-part, room temperature cure
- Manganese dioxide cured polysulfide
- Thixotropic (low sag)
- Recommend CS 900 adhesion promoter for acrylic and polycarbonate substrates

Flamemaster specification

- Based on AMS3333 (Type II, high strength)

13576 Desmond Street - Pacoima, CA 91331 (USA)
Phone: 818 890-1401 - Fax: 818 890-6001 - Email: sales@flamemaster.com