SHIMS & SEALANTS

flamemaster

SOCOMORE Aerospace Sealants



CS 415


Aerodynamic smoothing compound (CS 2415 replacement)

SAMPLES AVAILABLE

Features

- High strength: > 50 pli on multiple substrates
- Aluminium color
- Faster cure
- 98% NVM, minimum
- No APEO surfactants
- Terphenyl free
- No aromatic solvents

	Tack-free time (hours)	**Cure time to 35A** (hours)
B-1/2	< 5	< 24
B-2	< 12	< 36



Description

- Two-part, room temperature cure
- Manganese dioxide cured polysulfide
- Thixotropic (low sag)

Flamemaster specification

- Based on MIL-S-38228 and other customer requirements

FLAMEMASTER - > CS 415 leaflet - 04/2025

13576 Desmond Street - Pacoima, CA 91331 (USA)
Phone: 818 890-1401 - Fax: 818 890-6001 - Email: sales@flamemaster.com